



TITANIUM DS COMPETIOR PRODUCTS REFERENCE GUIDE

Products	MFG	Visible Light Transmittance	Visible Light Reflectance Interior	Visible Light Reflectance Exterior	UV Rejected	IR Rejected @980nm	Total Solar Energy Rejected
Titanium DS 20	Midas Window Film	23%	27%	28%	99%		65%
-	Vista						
N-1020	Llumar	24%	28%	29%	99%		63%
Neultral 20	3M	16%	17%	17%	99%		66%
-	Sunscape						
Daylight Natural 20	Johnson	22%					61%
Titanium DS 35	Midas Window Film	40%	16%	17%	99%		53%
V33	Vista	33%	19%	22%	99%		54%
N-1040	Llumar	40%	15%	18%	99%		50%
Neutral 35	3M	36%	16%	20%	99%		56%
Designer Gray-35	Sunscape	38%	17%	24%	99%		54%
Daylight Natural 35	Johnson	37%			99%		46%
Titanium DS 50	Midas Window Film	49%	11%	12%	99%		64%
V45	Vista	43%	14%	17%	99%		47%
N-1050	Llumar	49%	12%	14%	99%		42%
Neutral 50	3M	51%	11%	15%	99%		43%
Designer Gray-50	Sunscape	46%	13%	16%	99%		46%
Daylight Natural 50	Johnson	49%			99%		40%