



MIDAS WINDOW FILM™

THANKS FOR TRUSTING US!

	Visible Light Transmittance	Total Solar Transmittance	Total Solar Reflectance	Total Solar Absorbance	Visible Light Reflectance	Winter U-Value	UV Rejected	Glare Reduction	Shading Coefficient	Total Solar Energy Rejected	Film Gauge (Mils)	Structure	Peel Strength (pi)	Tensile Strength (psi)	
Clear Films															
2Mil	88%	75%	8%	17%	10%	1.05	99%	N/A	0.93	19%	2	1 ply	5	25,000	
4Mil	86%	74%	8%	18%	10%	1.05	99%	N/A	0.92	20%	4	1 ply	5	25,000	
7Mil	85%	71%	10%	19%	10%	1.05	99%	N/A	0.91	20%	7	1 ply	5	25,000	
8Mil	83%	77%	8%	15%	10%	1.05	99%	N/A	0.92	19%	8	2 ply	5	25,000	
11Mil	82%	70%	10%	20%	10%	1.05	99%	N/A	0.91	22%	11	2 ply	5	25,000	
16Mil	82%	70%	9%	21%	10%	1.05	99%	N/A	0.9	25%	14	2 ply	5	25,000	
21Mil	79%	65%	12%	23%	12%	1.01	99%	N/A	0.88	27%	21	3 ply	5	25,000	
4M Anti-Graffiti	86%	78%	9%	13%	9%	1.09	99%	3	0.95	19%	4	1 ply	5	25,000	
6M Anti-Graffiti	86%	76%	10%	14%	10%	1.09	99%	3	0.94	19%	6	1 ply	5	25,000	
Solar Films															
4Mil Titanium	65%	54%	10%	36%	11%	14%	1.06	99%	27%	0.7	40%	4	2 ply	5	25,000
4Mil Titanium	35%	26%	31%	43%	18%	27%	1.03	99%	58%	0.42	60%	4	3 ply	5	25,000
6Mil Titanium	35%	26%	31%	43%	18%	27%	1.03	99%	58%	0.42	60%	6	3 ply	5	25,000
6Mil Titanium	27%	19%	36%	45%	20%	35%	1.03	99%	70%	0.36	67%	6	3 ply	5	25,000
10Mil Titanium	47%	34%	23%	43%	12%	16%	1.06	99%	48%	0.55	50%	10	3 ply	5	25,000
10Mil Titanium	35%	26%	31%	43%	18%	27%	1.03	99%	58%	0.42	60%	10	3 ply	5	25,000
8.5 Mil 40% SolarGlaze	38%	29%	22%	49%	14%	17%	1.04	99%	57%	0.46	60%	8.5	3 ply	5	25,000
4Mil 20% Silver	15%	12%	55%	33%	58%	60%	0.94	99%	84%	0.25	79%	4	3 ply	5	25,000
8Mil 20% Silver	15%	12%	55%	33%	58%	60%	0.94	99%	84%	0.25	79%	8	3 ply	5	25,000